

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (withdrawn): A calcium tartrate composition comprising particles having a mean particle size less than about 30 μm .

2. (withdrawn): The composition according to claim 1, wherein the mean particle size is less than about 25 μm .

3. (withdrawn): The composition according to claim 1, wherein the mean particle size is less than about 20 μm .

4. (withdrawn): The composition according to claim 1, wherein the mean particle size is less than about 18 μm .

5. (withdrawn): The composition according to claim 1, wherein the mean particle size is less than about 15 μm .

6. (withdrawn): The composition of claim 1, wherein less than 5% of particles have a particle size greater than about 40 μm .

7. (withdrawn): The composition of claim 6, wherein less than 1% of particles have a particle size greater than about 40 μm .

8. (withdrawn): The composition of claim 6, wherein less than 0.1% of particles have a particle size greater than about 40 μm .

9. (withdrawn): A method for preparing a calcium tartrate composition comprising particles having a mean particle size less than about 30 μm , comprising the following steps:

submitting maleic acid to an enzymatic catalytic epoxidation thereby obtaining cis-epoxysuccinate,

submitting said cis-epoxysuccinate to the action of an epoxide hydrolase thereby producing L-tartaric acid;

precipitating said L-tartaric acid with CaCl_2 thereby obtaining calcium tartrate crystals; and

recovering the calcium tartrate crystals to obtain a calcium tartrate composition.

10. (withdrawn): The method of claim 9, wherein said L-tartaric acid is precipitated by adding an equimolar amount of CaCl_2 .

11. (withdrawn): The method of claim 9 further comprising drying and grinding said recovered calcium tartrate crystals.

12. (currently amended): A plaster composition comprising ~~the composition of claim 1~~ calcium tartrate particles having a mean particle size less than about 30 μm .

13. (currently amended): A powder comprising ~~the composition of claim 1~~ calcium tartrate particles having a mean particle size less than about 30 μm , wherein the powder is selected from the group consisting of cement, mortar, and concrete.

14. (withdrawn): A method for preparing a calcium tartrate composition comprising particles having a mean particle size less than about 18 μm , comprising the following steps:

submitting maleic acid to an enzymatic catalytic epoxidation thereby obtaining cis-epoxysuccinate,

submitting said cis-epoxysuccinate to the action of an epoxide hydrolase thereby producing L-tartaric acid;

precipitating said L-tartaric acid with CaCl_2 thereby obtaining calcium tartrate crystals; and

recovering the calcium tartrate crystals to obtain a calcium tartrate composition.

15. (withdrawn): The method of claim 14, wherein said L-tartaric acid is precipitated by adding an equimolar amount of CaCl_2 .

16. (withdrawn): The method of claim 14 further comprising drying and grinding said recovered calcium tartrate crystals.

AI
C
17. (currently amended): A plaster composition comprising ~~the composition of claim 4~~ calcium tartrate particles having a mean particle size less than about 18 μ m.

18. (currently amended): A powder comprising ~~the composition of claim 4~~ calcium tartrate particles having a mean particle size less than about 18 μ m, wherein the powder is selected from the group consisting of cement, mortar, and concrete.
